


**LOCTITE®**



# **LOCTITE 3D IND475™**

A60 High Rebound

Photoelastic

White, Black

**LOCTITE®**

Henkel Corporation


[loctite3dp@henkel.com](mailto:loctite3dp@henkel.com)





## IND475™

A60 HIGH REBOUND  
PHOTOELASTIC  
WHITE, BLACK



## LOCTITE 3D IND475™

LOCTITE 3D IND475 is a single component UV resin that cures to a soft, elastomeric material.

LOCTITE 3D IND475 is a flexible material that gives a good balance of hardness, strength and elongation.

LOCTITE 3D IND475 is a low viscosity liquid, printable at room temperature across various DLP platforms.



### Benefits:

- True elastomeric behavior
- Fast Printing with low shrinkage behavior
- High resilience / High energy return





### Ideal for:

- Air and dust gaskets
- Flexible seals and housings
- Cushioning pads



### Markets:



*\*Values shown are linked to LOCTITE IND475 White as reference, please refer to the specific mechanical properties for each of the colors shown in this document*





## IND475™

A60 HIGH REBOUND  
PHOTOELASTIC  
WHITE



## MECHANICAL PROPERTIES

| Mechanical Properties    | Measure           | Method     | Green | Post Processed            |
|--------------------------|-------------------|------------|-------|---------------------------|
| Tensile Stress at Break  | MPa               | ASTM D638  | -     | 3.1 ± 0.3 <sup>[1]</sup>  |
| Young's Modulus          | MPa               | ASTM D638  | -     | 1.1 ± 0.5 <sup>[1]</sup>  |
| Elongation at Break      | %                 | ASTM D638  | -     | 201 ± 16 <sup>[1]</sup>   |
| Tear Strength            | kN/m              | ASTM D624  | -     | 12.6 ± 0.6 <sup>[2]</sup> |
| Energy Return            | %                 | Internal   | -     | 55 <sup>[3]</sup>         |
| <b>Other Properties</b>  |                   |            |       |                           |
| Shore Hardness (0s, 5s)  | A                 | ASTM D2240 | -     | 57, 42 <sup>[4]</sup>     |
| Solid Density (Green)    | g/cm <sup>3</sup> | ASTM D792  | -     | 1.43 <sup>[5]</sup>       |
| Solid Density (Cured)    | g/cm <sup>3</sup> | ASTM D792  | -     | 1.04 <sup>[5]</sup>       |
| Volumetric Shrinkage     | %                 | Internal   | -     | -27 <sup>[5]</sup>        |
| Water Absorption (24hr)  | %                 | ASTM D570  | -     | 2.1 ± 0.1 <sup>[6]</sup>  |
| Water Absorption (72hr)  | %                 | ASTM D570  | -     | 4.5 ± 0.1 <sup>[6]</sup>  |
| Water Absorption (168hr) | %                 | ASTM D570  | -     | 6.5 ± 0.1 <sup>[6]</sup>  |

| Liquid Properties       | Measure           | Method     | Value                |
|-------------------------|-------------------|------------|----------------------|
| Viscosity @ 25°C (77°F) | cP                | ASTM D7867 | 1,400 <sup>[7]</sup> |
| Liquid Density          | g/cm <sup>3</sup> | ASTM D1475 | 1.02 <sup>[5]</sup>  |

\*All specimen are printed unless otherwise noted. All specimen were conditioned in ambient lab conditions at 19-23°C / 40-60% RH for at least 24 hours.\* ASTM Methods: D638 Type IV, 5 mm/min, D790-B, 2 mm/min, D648, D256 Notched IZOD (Machine Notched), 6 mm x 12 mm, D570 0.125" x 2" Disc 24hr@ 25°C, D2240, Type "D" (0, 3 seconds), D7867, D1475


**Internal Data Sources:**

[1] FOR22878, [2] FOR22879, [3] FOR22952, [4] FOR22950, [5] FOR23307, [6] FOR22955, [7] FOR22875





**IND475™**  
**A60 HIGH REBOUND**  
**PHOTOELASTIC**  
**WHITE**



## WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

## PRINTER SETTINGS

**LOCTITE 3D IND475 White** is formulated to print optimally on industrial DLP printer. Read the safety data sheet carefully to get details about health and safety instructions. Recommended print parameters:

- Shake resin bottle well before usage
- Temperature: 20°C to 30°C
- Intensity: 3 mW/cm<sup>2</sup> to 10 mW/cm<sup>2</sup>

### Exposure time for an intensity of 5 mW/cm<sup>2</sup>

|                           |     |                          |      |
|---------------------------|-----|--------------------------|------|
| Layer Thickness (µm):     | 100 | Ec (mJ/cm <sup>2</sup> ) | 3.55 |
| First layer time (s)      | 60  | Dp (mm):                 | 0.13 |
| Burn in region (s):       | 35  |                          |      |
| Model Layer Exposure (s): | 3.5 |                          |      |

## POST PROCESSING

**LOCTITE 3D IND475 White** requires post processing to achieve specified properties. Prior to post curing, support structures should be removed from the printed part, and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

| Post Process Step       | Agent | Method            | Duration | Intervals | Additional Info       |
|-------------------------|-------|-------------------|----------|-----------|-----------------------|
| Cleaning #1             | TPM   | Sonic             | 2 min    | 1         | LOCTITE® Cleaner T    |
| Cleaning #2             | IPA   | Sonic             | 2 min    | 1         | Use fresh IPA         |
| Dry                     | n.a.  | Compressed air    | 30 s     | 1         | Air pressure (30 psi) |
| Wait before post curing | n.a.  | Ambient condition | 60 min   | 1         | Room temperature      |

## POST CURING

**LOCTITE 3D IND475 White** requires **post curing in water** to achieve specified properties. It is recommended to apply a mold release on the parts before submerged in a transparent water container.

| UC Curing Unit      | UV Source                         | Intensity                              | Cure time/<br>side | Additional Settings<br>(Shelf, Output Energy) |
|---------------------|-----------------------------------|--|--------------------|---|
| Loctite UVALOC 1000 | Mercury Arc Bulb (broad spectrum) | 30 mW/cm <sup>2</sup> at 365 nm        | 5 min              | 500 W, 3 <sup>rd</sup> shelf from the top     |
| Dymax 5000 EC Flood | Mercury Arc Bulb (broad spectrum) | 150 - 175 mW/cm <sup>2</sup> at 380 nm | 10 min             | 400W, Shelf K                                 |
| Loctite CL36        | 405nm LED                         | 80 mW/cm <sup>2</sup> at 405 nm        | 90 min             | 100% top & side                               |





## IND475™

A60 HIGH REBOUND  
PHOTOELASTIC  
BLACK



## MECHANICAL PROPERTIES

| Mechanical Properties    | Measure           | Method     | Green | Post Processed           |
|--------------------------|-------------------|------------|-------|--------------------------|
| Tensile Stress at Break  | MPa               | ASTM D638  | -     | 2.4 ± 0.6 <sup>[1]</sup> |
| Young's Modulus          | MPa               | ASTM D638  | -     | 2.5 ± 0.3 <sup>[1]</sup> |
| Elongation at Break      | %                 | ASTM D638  | -     | 122 ± 11 <sup>[1]</sup>  |
| Tear Strength            | kN/m              | ASTM D624  | -     | 7.5 ± 1.2 <sup>[2]</sup> |
| Energy Return            | %                 | Internal   | -     | 77 ± 4 <sup>[3]</sup>    |
| <b>Other Properties</b>  |                   |            |       |                          |
| Shore Hardness (0s, 5s)  | A                 | ASTM D2240 | -     | 49, 45 <sup>[4]</sup>    |
| Solid Density (Green)    | g/cm <sup>3</sup> | ASTM D792  | -     | 1.16 <sup>[5]</sup>      |
| Solid Density (Cured)    | g/cm <sup>3</sup> | ASTM D792  | -     | 1.06 <sup>[5]</sup>      |
| Volumetric Shrinkage     | %                 | Internal   | -     | -9 <sup>[5]</sup>        |
| Water Absorption (24hr)  | %                 | ASTM D570  | -     | 3.2 <sup>[6]</sup>       |
| Water Absorption (72hr)  | %                 | ASTM D570  | -     | 5.4 <sup>[6]</sup>       |
| Water Absorption (168hr) | %                 | ASTM D570  | -     | 8.5 <sup>[6]</sup>       |

| Liquid Properties       | Measure           | Method     | Value                |
|-------------------------|-------------------|------------|----------------------|
| Viscosity @ 25°C (77°F) | cP                | ASTM D7867 | 1,500 <sup>[7]</sup> |
| Liquid Density          | g/cm <sup>3</sup> | ASTM D1475 | 1.01 <sup>[5]</sup>  |

\*All specimen are printed unless otherwise noted. All specimen were conditioned in ambient lab conditions at 19-23°C / 40-60% RH for at least 24 hours.\* ASTM Methods: D638 Type IV, 5 mm/min, D790-B, 2 mm/min, D648, D256 Notched IZOD (Machine Notched), 6 mm x 12 mm, D570 0.125" x 2" Disc 24hr@ 25°C, D2240, Type "D" (0, 3 seconds), D7867, D1475


**Internal Data Sources:**

[1] FOR40695, [2] FOR40696, [3] FOR40697, [4] FOR40692, [5] FOR35576, [6] FOR29248, [7] FOR40548





**IND475™**  
**A60 HIGH REBOUND**  
**PHOTOELASTIC**  
**BLACK**



## WORKFLOW

Validated workflows need to be followed to achieve properties as provided in the TDS. Examples of validated workflow steps are listed below. Users should defer to the most current workflow information for best results which can be found at <https://www.loctiteam.com/printer-validation-settings>

## PRINTER SETTINGS

**LOCTITE 3D IND475 Black** is formulated to print optimally on industrial DLP printer. Read the safety data sheet carefully to get details about health and safety instructions. Recommended print parameters:

- Shake resin bottle well before usage
- Temperature: 20°C to 30°C
- Intensity: 3 mW/cm<sup>2</sup> to 10 mW/cm<sup>2</sup>

### Exposure time for an intensity of 3 mW/cm<sup>2</sup>

|                           |     |                          |
|---------------------------|-----|--------------------------|
| Layer Thickness (µm):     | 100 | Ec (mJ/cm <sup>2</sup> ) |
| First layer time (s)      | 50  | Dp (mm):                 |
| Burn in region (s):       | 25  |                          |
| Model Layer Exposure (s): | 4.7 |                          |

## POST PROCESSING

**LOCTITE 3D IND475 Black** requires post processing to achieve specified properties. Prior to post curing, support structures should be removed from the printed part, and the part should then be washed. Use compressed air to remove residual solvent from the surface of the material between intervals.

| Post Process Step       | Agent | Method            | Duration | Intervals | Additional Info       |
|-------------------------|-------|-------------------|----------|-----------|-----------------------|
| Cleaning #1             | TPM   | Sonic             | 2 min    | 1         | LOCTITE® Cleaner T    |
| Cleaning #2             | IPA   | Sonic             | 2 min    | 1         | Use fresh IPA         |
| Dry                     | n/a   | Compressed air    | 30 s     | 1         | Air pressure (30 psi) |
| Wait before post curing | n/a   | Ambient condition | 60 min   | 1         | Room temperature      |

## POST CURING

**LOCTITE 3D IND475 Black** requires **post curing in water** to achieve specified properties. It is recommended to apply a mold release on the parts before submerged in a transparent water container.

| UC Curing Unit      | UV Source                         | Intensity                              | Cure time/ side | Additional Settings (Shelf, Output Energy) |
|---------------------|-----------------------------------|--|-----------------|--|
| Loctite UVALOC 1000 | Mercury Arc Bulb (broad spectrum) | 30 mW/cm <sup>2</sup> at 365 nm        | 10 min          | 500 W, 3 <sup>rd</sup> shelf from the top  |
| Dymax 5000 EC Flood | Mercury Arc Bulb (broad spectrum) | 150 - 175 mW/cm <sup>2</sup> at 380 nm | 10 min          | 400W, Shelf I                              |
| Nexa Cure           | 365nm and 405nm LED               | 20-25mW/cm <sup>2</sup>                | 60 min          | Middle shelf                               |








## IND475™

A60 HIGH REBOUND  
PHOTOELASTIC  
WHITE, BLACK



## Additional Workflow Notes

### PRINT SETTINGS

Printing with **LOCTITE® 3D IND475™** requires detailed attention to interactions between the material and the hardware in use. Mechanical process settings must be optimized for each printer based on the hardware and software capabilities. Due to the low durometer and high elasticity of the material, printed parts may sway during tray release, build head movement, and upon re-entering the resin. For this reason, the user must consider many variables while printing. Some applicable print process considerations and respective guidelines are discussed below. Critical considerations include adhesion behavior at the print interface, model geometry, and model print orientation.

**Lift Height Between Layers:** Larger parts may require larger lift heights due to overall elongation magnitude.

- Small parts (<25 mm height): 10-15mm
- Medium parts (25 - 100 mm height): 20-25 mm
- Large parts (>100mm height): 25-30 mm

**Build Head Movement Rates:** Thicker parts allow for more rapid rates due to overall part rigidity compared to printing forces.

- Low Thickness (<5mm thickness): 3-5 mm/second
- Medium Thickness (5-10 mm thickness): 3-10 mm/second
- High Thickness (>10 mm thickness): 3-20 mm/second

**Time Delay Before Layer Exposure:**

- Generally, 3-5 seconds is sufficient due to the resin's low viscosity. Parts with thin features may require longer times for the small features to return to the correct position as they normalize with the resin's viscosity forces.

**Support Structures:**

- Place supports on non-critical model surfaces if possible. Support structure placement and geometry is model-dependent based on model layer surface area. General recommendations are provided.
- Support Thickness: 0.6-0.8 mm diameter
- Support Contact Area: 25-75% support thickness

### POST PROCESSING

- **LOCTITE® 3D IND475™** requires post processing to achieve specified properties. Prior to post curing, the part should be washed in a friendly cleaner. We recommend in **LOCTITE® Cleaner T**.
- Post curing of **LOCTITE® 3D IND475™** to reach stated property targets must be cured in water or an alternative inert medium.
- Coating parts with a spray-on mold release agent such as **LOCTITE® Frekote 770-NC** or **Smooth-On Universal Mold Release** prior to post curing can reduce the surface tack of a final part. After curing, the mold release can be rinsed off with water or Isopropanol.


<https://www.loctiteam.com/printer-validation-settings/>





## IND475™

A60 HIGH REBOUND  
PHOTOELASTIC  
WHITE, BLACK



### NOTE

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of **Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.


#### Trademark Usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.





**LOCTITE®**



**FIND OUT MORE AT**

**LOCTITEAM.COM**

**LOCTITE®**

Henkel Corporation

[loctite3dp@henkel.com](mailto:loctite3dp@henkel.com)



Version 2021/07/15